



Sample Name: P18416-15S
14- arms Poly styrene




Core Poly butadiene




Branches of Polystyrene

Mn x 10 ³ (total)	PDI
75.0	1.07
Mn of each arm: (5.0)	

Synthesis Procedure:




Linker : PBd:




HNMNR of Branch

SEC of the Polymer: (eah branch of Polystyrene)
Sample ID: P18416-S Branch




Sample	Mn	Mw	Mp	Mw/Mn	IV
P18416-S_01.vdt	4,957	5,114	5,105	1.032	0.0617



Sample ID: P18416-S Star

Concentration (mg/mL)	6.3528
Sample dn/dc (mL/g)	0.1850
Method File	PS80K-Jan05-2014-0001.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18416-Star_Multiarm_01.vdt	75,367	80,951	80,734	1.074	0.0973

