


Sample Name: Deuterated Multiarm Polystyrene
Sample # P18522B-15dPS
15- arms Deuterated Poly styrene





Mn x 10^3 (total)	PDI
17.0 Mn of each arm: (1.1)	1.27


Synthesis Procedure:













Linker : Lot# P18516: Value of X 4 to 5 as average Mn 1100



SEC of the Polymer: (eah branch of Polystyrene)

Sample ID: P18522B-dPs Star

Concentration (mg/mL)	1.0285
Sample dn/dc (mL/g)	0.1700
Method File	PS80K-Feb25-2014-0000.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn	Mw	Mp	Mw/Mn	IV
P18522B-dPS_star_01.vdt	16,994	21,569	17,904	1.269	0.104