


## Sample Name: Deuterated Polystyrene (d<sub>3</sub>)

Sample #: P18727-d3PS

**Structure:**




**Composition:**

Mn x 10 <sup>3</sup>	PDI
90.0	1.3

### **Synthesis Procedure:**

Deuterated polystyrene-d<sub>3</sub> is obtained by living anionic polymerization of styrene-d<sub>3</sub> as illustrated below:



### **Characterization:**


The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors from Viscotek Co. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used.

### **Solubility:**

Deuterated polystyrene-d<sub>3</sub> is soluble in DMF, THF, toluene and CHCl<sub>3</sub>. It precipitates from methanol, ethanol, water and hexanes.

### SEC profile of the product:

**P18727-d<sub>3</sub>PS**



Size exclusion chromatograph of deuterated polystyrene(d3):

M<sub>n</sub>=90,000 M<sub>w</sub>=117,000 PI=1.3