


Sample Name:

Hydroxy Terminated Poly(2-Vinyl Pyridine)




Composition:

$M_n \times 10^3$	PDI
25.0	1.06
Functionality %	>99%
T _g for the functional polymer	94°C

Synthesis Procedure:

Hydroxy terminated poly(2-vinyl pyridine) was prepared by living anionic polymerization of 2-vinyl pyridine in THF using OH protected initiator. The scheme of the reaction is illustrated below:



Characterization:

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector.

Thermal analysis:

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of $10^{\circ}\text{C}/\text{min}$. The inflection glass transition temperature (T_g) has been considered.


Solubility:

Polymer is soluble in CHCl_3 and THF.

SEC of Sample:


Sample ID: P19122-2VPOH

Concentration (mg/mL)	2.3254
Sample dv/dc (mL/g)	0.1670
Method File	PS80K-Feb26-2015-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19122-2VPCH_01.vdt	25,097	26,545	25,616	1.058	0.3148

¹H NMR:



DSC thermogram for the sample:

