



Sample Name:

Tert.butyl dimethyl siloxy propyl Terminated
Poly(2-Vinyl Pyridine)
Sample #: P19249-tBuDMSPr2VP


Structure:**Composition:**

M _n x 10 ³	PDI
198.0	1.08
Functionality %	>99%


Synthesis Procedure:**SEC of Sample:**

Sample ID:P19249-2VPOH Protected

Concentration (mg/mL)	3.820
Sample dn/dc (mL/g)	0.1670
Method File	PS80K-April13-2015-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19249-2VPOH_protected_01.vdt	197,649	212,372	213,918	1.074	1.1822

**Characterization:**

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector.

Thermal analysis:

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T_g) has been considered.

Solubility:

Polymer is soluble in CHCl₃ and THF.