



Sample Name:

Tert.butyl dimethyl siloxy propyl Terminated
Poly(2-Vinyl Pyridine)
Sample #: P19250-tBuDMSPr2VP

Structure:**Composition:**

| $M_n \times 10^3$ | PDI |
|-------------------|------|
| 31.0 | 1.06 |
| Functionality % | >99% |

Synthesis Procedure:**Characterization:**

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector.

Thermal analysis:

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T_g) has been considered.


Solubility:

Polymer is soluble in CHCl_3 and THF.

SEC of Sample:

Sample ID:P19250-2VPOH protected

| | |
|-----------------------|-----------------------------|
| Concentration (mg/mL) | 0.4419 |
| Sample dn/dc (mL/g) | 0.1670 |
| Method File | PS80K-April13-2015-0000.vcm |
| Column Set | 3x PL 1113-6300 |
| Solvent | THF |



| Sample | MW Number Average (Da) | MW Weight Average (Da) | MW at Peak (Da) | Polydispersity | Intrinsic Viscosity (dL/g) |
|---------------|------------------------|------------------------|-----------------|----------------|----------------------------|
| P19250_01.vdt | 31,069 | 33,163 | 31,466 | 1.057 | 0.3621 |