



Sample Name:**Carboxy Terminated Poly(t-butyl acrylate)****Sample #: P1937-tBuACOOH****Structure:****Composition:**

$M_n \times 10^3$	PDI
4.2	1.25
Functionality	>95%
T_g for the polymer	28°C

Synthesis Procedure:

Carboxy terminated poly(t-butyl acrylate) is synthesized by living anionic polymerization of methyl methacrylate followed by termination with dry ice.

**Characterization:**


The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) before inclusion of the CO_2H function using a Varian liquid chromatograph equipped with a UV and refractive index detector. The functionality of polymer was determined by the titration with NaOH, using phenolphthalein as the indicator.

Thermal analysis:

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of $10^\circ\text{C}/\text{min}$. The inflection glass transition temperature (T_g) has been considered.

Solubility:

The functionalized polymer is soluble in THF, toluene and chloroform. It precipitates into Methanol/water mixture.

SEC of Sample:

Size exclusion chromatography of a-w dicarboxy terminated poly(tert.butylacrylate) (before terminating reaction with CO_2).

$M_n=4200$, $M_w=5200$ PI=1.25, functionality=0.95

DSC thermogram for the sample: