


SEC of Bd-Ip diblock copolymer:

Sample ID-P19573-BdIP

Concentration (mg/mL)	0.4252
Sample dn/dc (mL/g)	0.1320
Method File	PS80K-Nov-2015-0000.vom
Column Set	3x PL 1113-6300
Solvent	THF




Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19573-2_01.vdt	264,340	411,073	394,344	1.555	23.8731

SEC of Bd-Ip-Bd triblock copolymer:

Sample ID-P19573-BdIPBd

Concentration (mg/mL)	0.2448
Sample dn/dc (mL/g)	0.1860
Method File	PS80K-Nov-2015-0000.vom
Column Set	3x PL 1113-6300
Solvent	THF



Sample	MW Number Average (Da)	MW Weight Average (Da)	MW at Peak (Da)	Polydispersity	Intrinsic Viscosity (dL/g)
P19573-3_01(790).vdt	282,202	310,457	311,232	1.100	36.5308