


**Sample Name: Hydroxy Terminated
Poly(9-Anthracenyl methyl methacrylate)**

Sample #: P19760-9AnMMA-OH

Structure:



Composition:

$M_n \times 10^3$	PDI
13.0	1.45


Synthesis Procedure:

The polymer was synthesized by anionic process.

Characterization:

The polymer was characterized by SEC and ^1H NMR


^1H NMR spectrum of the polymer:



SEC elugram of the polymer:

Sample ID: P19760-9AnMMA

Concentration (mg/mL)	8.1871
Sample dn/dc (mL/g)	0.0940
Method File	PS80K-March2016-0001.vcm
Column Set	3x PL 1113-6300
Solvent	THF



: