


Sample Name: Poly(1,4-butadiene-b- ϵ -caprolactone)

Sample #: P2081-BdCL

Structure:




Composition:

Mn $\times 10^3$ Bd-b-CL	Mw/Mn (PDI)
11.5-b-18.0	1.10

Synthesis Procedure:

Poly(1,4-butadiene-b- ϵ -caprolactone) is prepared by living anionic polymerization addition of butadiene followed coordination polymerization of ϵ -caprolactone. The reaction scheme is shown below:




Characterization:

An aliquot of the anionic poly(butadiene) block was terminated before addition of ϵ -caprolactone and analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The final block copolymer composition was calculated from $^1\text{H-NMR}$ spectroscopy by comparing the peak area of the vinylic butadiene protons at about 5.4 ppm with the ϵ -caprolactone protons at about 4.1 ppm. Block copolymer PDI is determined by SEC.

Solubility:

The polymer is soluble in tetrahydrofuran (THF) and chloroform (CHCl_3).

$^1\text{H NMR}$ of the block polymer:




Thermal analysis of the sample# P2081-BdCL

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Melting and crystallization curve for the sample

The melting temperature (T_m) was taken as the maximum of the endothermic peak where as the crystallization temperature (T_c) was considered as the minimum of the exothermic peak.

Thermogram for Bd block:



Thermal analysis results at a glance:

Sample	T_m (°C)	T_c (°C)	T_g (°C)
Bd block	-	-	-75
CL block	61	23	Not distinct

Thermogram for ε-caprolactone block:

