



¹H-NMR Spectrum of the random copolymer:




SEC for the polymer



Size exclusion chromatograph of random copolymer of Poly(styrene-co-p chloromethylstyrene):

$M_n = 29200$, $M_w = 33000$ $M_w/M_n = 1.12$

DSC thermogram for the sample




Sample Name:

Random Copolymer Poly(styrene-co-p-chloromethyl styrene)

Sample #: P2128 SSMeClran

Structure:



Composition:

PSMeCl (mol%) : 5.33

$M_n \times 10^3$	PDI
PS-co-PSMeCl	
29.2	1.12
T_g for random polymer	103°C

Synthesis Procedure:

Random Copolymer Poly(styrene-co-p-chloromethyl styrene) is prepared by radical polymerization of styrene and p-chloromethyl styrene in the presence of TEMPO .

Characterization:

The polymer was analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The copolymer composition was calculated from ¹H-NMR spectroscopy by comparing the peak area the aromatic protons of styrene at about 7.05 ppm with the protons of chloromethyl styrene at about 4.6 ppm.

Thermal analysis:

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility:

Random Copolymer Poly(styrene-co-methyl methacrylate) is soluble in CHCl₃, THF, DMF, toluene and precipitated out from methanol.