


Sample Name:

**α -Carboxyl- ω -Hydroxyl Terminated Poly(ethylene glycol),
isopropyl spacer**

Sample#: P2425-HOEGCOOH

Structure:



Composition:

Mn x 10 ³	PDI
2.1	1.37

Synthesis Procedure:

α -Carboxy ω -Hydroxy terminated poly(ethylene glycol) was synthesized by a simple procedure discovered in our lab. The details can be found in the US patent published.¹

Characterization:


The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector.

Functionality: Functionality of the polymer was determined by acid base titration and from H NMR analysis.

Solubility:

Polymer is soluble in water, methanol and ethanol, THF, CHCl₃. It is precipitated out from cold ethanol, isopropanol, hexane and ether.

SEC of Sample:



Size Exclusion Chromatography profile of the product:
M_n = 1600 (SEC w.r.t PEG calibration), M_n/M_w = 1.12
Mn: by titration (2000)

Reference (s):

S. K. Varshney, J.X. Zhang, US patent 7,009,033 B2, 2006
Assigned to Polymer source, Inc. Canada
Heterofunctional Polyethylene glycol and Poly ethylene oxide ,
process for their Manufacture