


Sample Name:

**Hydroxy Terminated Poly(ethyl acrylate)**

Sample #: **P2606-EtAOH**

**Structure:**




**Composition:**

|                      |      |
|----------------------|------|
| Mn x 10 <sup>3</sup> | PDI  |
| 11.6                 | 1.12 |
| T <sub>g</sub> (°C)  | -19  |

**Synthesis Procedure:**

Hydroxy Terminated Poly(ethyl acrylate) is synthesized by living anionic polymerization of t-butyl acrylate using a hydroxyl protected initiator such as tert-butyl dimethyl siloxy propyl lithium. The obtained polymer was transesterified in the presence of acid and ethanol.



**Characterization:**

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector.


**Thermal Analysis:**

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T<sub>g</sub>) of the sample has been considered.

**Solubility:**

Polymer is soluble in THF, CHCl<sub>3</sub>. It is precipitated out from cold ethanol, methanol cold and water.

**SEC of Sample:**



Size exclusion chromatograph of Hydroxy Terminated Poly(ethyl acrylate):

M<sub>n</sub>=11600, M<sub>w</sub>=13000, PI=1.12

**DSC thermogram for the polymer:**

