


Sample Name: Poly carbonate
(Bisphenol-A carbonate)
Sample #: P3783-PC

Structure:



Composition:


Mn 10 ³	Mw/Mn
22.0	1.9

Characterization :

By SEC in THF

SEC:

P3783-PC



Size exclusion chromatography of polycarbonate
(Bisphenol-A-carbonate):

$M_w=43500$, $M_n=22000$ PI=1.9 Solution Viscosity: in THF at 35 oC: 0.45 dl/g

Radius of Gyration: 7.4 nm