


## Sample Name: Poly(n-nonyl acrylate)

Sample #: P6313-nNA

Structure:




Composition:

$M_n \times 10^3$	PDI
13.0	1.5

Synthesis Procedure:

Poly(n-nonyl acrylate) is obtained by group transfer polymerization (GTP) of n-nonyl acrylate. The reaction scheme is shown below:



Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Solubility:

Poly(n-butyl acrylate) is soluble in THF, toluene and  $\text{CHCl}_3$ . This polymer precipitates from ethanol and methanol containing 10-15% water.

SEC of the Homopolymer:

