


Sample Name:

Random Copolymer Poly(styrene-co-4-vinylpyridine)


Sample #: P7305-S4VPran**Structure:****Composition:**

P4VP (mol%) : 37

Mn x 10 ³ PS-co-P4VP	PDI
59.2	1.6
T _g for random polymer	122°C

Synthesis Procedure:

The polymer is prepared by radical polymerization of styrene and 4-vinylpyridine in the presence of TEMPO. The scheme of the reaction is illustrated below:

**Characterization:**


The polymer was analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The copolymer composition was calculated from ¹H-NMR spectroscopy by comparing the peak area of 4VP protons at 8.28 ppm with the styrene protons at about 6.1-7.2 ppm that deducts the contribution of the 4VP protons.

Thermal analysis:


Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility:

The polymer is soluble in CHCl₃, THF, DMF, toluene and precipitated out from hexane

¹H-NMR Spectrum of the random copolymer:**SEC of the random copolymer:**

P7305-S4VPran



M_n=59200, M_w=94700, PI=1.6 (SEC polystyrene standard)
4VP%mol=37% from NMR

Thermogram for the sample: