


Sample Name:

Random Copolymer Poly(styrene-co-methyl methacrylate), α -Hydroxyl- ω -Tempo moiety Terminated

Sample #: P7343A-SMMAran-OHT

Structure:




Composition:

$M_n \times 10^3$ (Styrene content mol%)	M_w/M_n (PDI)
15.0 (58%)	1.20

Synthesis Procedure:

Hydroxy terminated poly(styrene-co-methyl methacrylate) is prepared by stable free radical polymerization at 135°C. The reaction scheme is shown below:



Characterization:

An aliquot of the copolymer was analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI), the instrument calibrated by Polystyrene standards. The chemical composition was calculated from $^1\text{H-NMR}$ spectroscopy by comparing the peak area of the phenyl protons at 6.8-7.4 ppm with the peak area of methyl methacrylate at 2.6-3.6 ppm.

Solubility:

Poly(styrene-co-methyl methacrylate) is soluble in THF, DMF, Toluene and chloroform. Precipitate from methanol and Hexanes.

Figure: $^1\text{H-NMR}$ spectrum





Figure: SEC profile of the random copolymer

P7343A-SMMAran-OHT



Size exclusion chromatograph of random copolymer: poly(styrene-co-MMA):

$M_n=15,000$, $M_w=18,000$, $M_w/M_n=1.20$
Polystyrene content: 58 mol% by NMR