


Sample Name: Oligomers of Poly(t-butyl acrylate)

Sample #: P8429-tBuA

Structure:



Composition:

Degree of Polymerization	PDI
Dp: by HNMR: 9	1.16
DP by MALDI-TOFF 5	

Synthesis Procedure:

Poly(t-butyl acrylate) is obtained by living anionic polymerization of t-butyl acrylate.¹⁻⁴

Characterization:


The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T_g) of the sample has been considered.

Solubility:

Poly(t-butyl acrylate) is soluble in THF, hexanes (low MW), toluene and CHCl₃. This polymer precipitates from ethanol and methanol containing 10-15% water.

H NMR of the Polymer




MALDI-TOFF analysis:


Error! Objects cannot be created from editing field codes.

SEC of Sample:

P8429-tBuA Oligomer



Tg of poly t-butyl acrylate as function of molecular weight



References:

- Ph. Teyssié, Ph. Bayard, R. Jerome, **S. K. Varshney**, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules*” 1994, 67.
- R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssié and **S. K. Varshney**, *Macromolecules*, 1987, 20, 1442-1444.
- Jerome, R. Forte, **S. K. Varshney**, R. Fayt, and Ph. Teyssié, "The Anionic Polymerization of Alkylacrylates:A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanaille and A. Guyot Ed., NATO ASI Series C 215,101 (1987), CA Vol. 108, 12, 094992.
- Ph. Teyssié, R. Fayt, C. Jacobs, R. Jerome, L. Leemans, and **S. K. Varshney** *Am. Chem. Soc., Polym. Prepr.* 1988, 28, 2, 52-53